



Concure Admix

INTEGRAL PERMANENT WATERPROOFING

DESCRIPTION

Concure Admix is a liquid, water-based, waterproofing additive used to replace externally applied treatments for protecting concrete structures against moisture transmission. Concure Admix is added to the concrete mix at the batch plant or added on site. Concure Admix becomes an integral and permanent part of the concrete slab.

ADVANTAGES

- Improves freeze/thaw resistance
- Keeps concrete from dusting
- Inhibits rusting of metal reinforcing bar
- Offers faster finishing time
- Reduces shrinkage cracks
- Maintains good flexibility at low slump
- Prevents capillary action
- Stops water, salt and alkali intrusion
- Resistant to chemical and acid-attack
- Helps reduce radon gas
- Can be used in stained and colored concrete
- Reduces Alkali-Silica-Reactivity (ASR)
- Compatible with adhesives coatings and paints

APPLICATIONS

Concure Admix eliminates moisture problems, increases strength, and reduce curling and hairline cracks. Concure Admix accelerates the concrete curing process to allow floor covering more quickly.

TECHNICAL

Concure Admix is environmentally safe and contains no VOC.

Appearance: Colorless
 Odor: None
 Toxicity: None
 Flammability: None
 Shelf Life: Indefinite
 Weight: 9 lbs. 2 oz. / gallon

Storage Temperature: Above 45°F (8°C)
 Solvent: Water
 Hazardous Vapor: None
 Membrane Type: CSH
 Installation: All Grade Levels

ASTM	METHOD	RESULTS
D5084	Hydrostatic Permeability	1.12 X 10 ⁻⁸ cm/sec
C1567	Alkali-Silica Reactivity	-0.009 Percent (Control +0.024%)
C39	Compressive Strength	125 Percent of Control
C78	Flexural Strength	117 Percent of Control
C157	Drying Shrinkage	No effect

LIMITATIONS

A Concure representative should be present at the jobsite during mixing and placement of the first batch of treated concrete.

Use non-chloride additives such as accelerators, plasticizers and water reducers with Concure

Admix. Retarders may be used when ambient temperatures exceed 75°F (24°C).

Use Concure Admix is used place of a portion of the mix water. A water-to-cement ratio (w/c) of .45 or less is critical to performance. Plasticizer and/or water reducing admixtures are recommended to achieve greater than 4" (100 mm) slump.

Store above 45°F (8°C), do not allow freezing. Separation may occur at temperatures less than 45°F (8°C) and thorough agitation will be required.

PACKAGING

55 Gallon Drums
 275 Gallon Totes
 5 Gallon Pails



Concure Admix

INTEGRAL PERMANENT WATERPROOFING

1 gallon units available upon request(min. order req.)

PRECAUTIONS

Avoid using paraffin or petroleum based curing agents as they need to be mechanically removed, substrate skim coated prior to installations.

NOTE: Concure Admix & DermaShield are compatible with all finished floor coverings and coatings

The Concure Group recommends following established ACI /Resilient Flooring Institute guidelines for curing. Complete installation recommendations are available from the flooring manufacturer

A representative of The Concure Group can be present, upon request, at the Batch/Jobsite during dosing/mixing and placement for the initial major concrete placement. If additives are required or needed, use non- chloride products. Retarders can be used when weather conditions require a retarder to be used (i.e. - high temp, high humidity).

MIXING AND APPLICATION

Concure Admix is added at the batch plant or at the job site at a rate of 14 ounces (397g) per 100 pounds of cement plus any other binder. Additional dosage may be required for greater high early strength benefits.

TRUCK OR PLANT MIXING:

The dosage accuracy of any admixture should be within plus or minus 3%. Two or more admixtures may be used in the same concrete batch, provided admixtures are added separately and that the combination has no deleterious effect on the concrete. After Concure Admix addition, rotate drum for 7 minutes, RAPID MIXING, before dispensing concrete.

ON-SITE MIXING:

Add the Concure Admix to the concrete truck and let drum rotate for 7 minutes, RAPID MIXING, before dispensing concrete.

WARRANTY AND DISCLAIMER

Extended Warranties are available. Written extended warranties are available on a per job basis.

If an extended warranty is required, the following items must be supplied to The Concure Group –

D-Scope meeting should be scheduled prior to the pour to discuss the following –

- a. Mix Design
- b. Batch Plant quality control testing
- c. Concrete Contractor participation in finishing and curing
- d. Submission of all materials to be used on sealed concrete surface
- e. GC acknowledgements

Please call for further information